



TESNIT® BA-R



TESNIT® BA-R has very good mechanical properties (resistance to high internal and surface pressure). TESNIT® BA-R is designed for the automotive and engine-building industries.

PROPERTIES

| | | | |
|-----------|-----------------------|-------------------------|---------------------|
| SUPERIOR | | | |
| EXCELLENT | MECHANICAL RESISTANCE | | |
| VERY GOOD | | | |
| GOOD | Thermal Resistance | Sealability Performance | Chemical Resistance |
| Moderate | | | |

APPROPRIATE INDUSTRIES & APPLICATIONS

- AUTOMOTIVE AND ENGINE BUILDING INDUSTRY
- SHIPBUILDING

| | | |
|-------------|--|--|
| Composition | Aramid fibres, inorganic fillers, NBR binder, carbon steel wire mesh insert. | |
| Colour | Black | |
| Approvals | BAM (Oxygen) Germanischer Lloyd | |


TECHNICAL DATA

Typical values for a thickness of 2 mm

| | | | |
|---|-------------|-------------------|----------|
| Density | DIN 28090-2 | g/cm ³ | 2.0 |
| Compressibility | ASTM F36J | % | 8 |
| Recovery | ASTM F36J | % | 55 |
| Tensile strength | ASTM F152 | MPa | 17 |
| Stress resistance | DIN 52913 | | |
| 16 h, 50 MPa, 175 °C | | MPa | 30 |
| 16 h, 50 MPa, 300 °C | | MPa | 25 |
| Specific leak rate | DIN 3535-6 | mg/(s·m) | / |
| Thickness increase | ASTM F146 | | |
| Oil IRM 903, 5 h, 150 °C | | % | 8 |
| ASTM Fuel B, 5 h, 23 °C | | % | / |
| Compression modulus | DIN 28090-2 | | |
| At room temperature: ϵ_{KSW} | | % | 8.5 |
| At elevated temperature: $\epsilon_{WSW/200\text{ }^{\circ}\text{C}}$ | | % | 15.8 |
| Percentage creep relaxation | DIN 28090-2 | | |
| At room temperature: ϵ_{KRW} | | % | 4.2 |
| At elevated temperature: $\epsilon_{WRW/200\text{ }^{\circ}\text{C}}$ | | % | 0.7 |
| Max. operating conditions | | | |
| Peak temperature | | °C/°F | 400/752 |
| Continuous temperature | | °C/°F | 350/662 |
| - with steam | | °C/°F | / |
| Pressure | | bar/psi | 140/2030 |

P-T DIAGRAM

EN 1514-1, Type IBC, PN 40, DIN 28091-2 / 3.8, 2.0 mm



- General suitability - Under common installation practices and chemical compatibility.
- Conditional suitability - Appropriate measures ensure maximum performance for joint design and gasket installation. Technical consultation is recommended.
- Limited suitability - Technical consultation is mandatory.

| | |
|------------------------------|--|
| Surface finish | Standard: 2G. Optional: graphite or PTFE. |
| Standard dimension of sheets | Size (mm): 1000 x 1500 1500 x 1500 Thickness (mm): 1.0 1.5 2.0 3.0 Other sizes and thicknesses available on request. |
| Tolerances | On length and width: $\pm 5\%$ On thickness up to 1.0 mm: ± 0.1 mm On thickness above 1.0 mm: $\pm 10\%$ |

| | |
|-----------------------------|---|
| Acetamide | + |
| Acetic acid, 10% | - |
| Acetic acid, 100% (Glacial) | - |
| Acetone | ? |
| Acetonitrile | - |
| Acetylene (gas) | + |
| Acid chlorides | - |
| Acrylic acid | - |
| Acrylonitrile | - |
| Adipic acid | - |
| Air (gas) | + |
| Alcohols | + |
| Aldehydes | ? |
| Alum | ? |
| Aluminium acetate | - |
| Aluminium chloride | - |
| Aluminium chloride | - |
| Aluminium sulfate | - |
| Amines | - |
| Ammonia (gas) | ? |
| Ammonium bicarbonate | + |
| Ammonium chloride | - |
| Ammonium hydroxide | + |
| Amyl acetate | ? |
| Anhydrides | - |
| Aniline | - |
| Anisole | ? |
| Argon (gas) | + |
| Asphalt | + |
| Barium chloride | - |
| Benzaldehyde | - |
| Benzene | + |
| Benzoic acid | ? |
| Bio-diesel | + |
| Bio-ethanol | + |
| Black liquor | - |
| Borax | + |
| Boric acid | - |
| Butadiene (gas) | + |
| Butane (gas) | + |
| Butyl alcohol (Butanol) | + |
| Butyric acid | - |
| Calcium chloride | - |
| Calcium hydroxide | + |
| Carbon dioxide (gas) | + |
| Carbon monoxide (gas) | + |
| Cellosolve | ? |
| Chlorine (gas) | - |
| Chlorine (in water) | - |
| Chlorobenzene | ? |
| Chloroform | - |
| Chloroprene | ? |
| Chlorosilanes | - |
| Chromic acid | - |
| Citric acid | - |
| Copper acetate | - |
| Copper sulfate | - |
| Creosote | ? |
| Cresols (Cresylic acid) | - |
| Cyclohexane | + |
| Cyclohexanol | + |
| Cyclohexanone | ? |
| Decalin | + |
| Dextrin | + |
| Dibenzyl ether | ? |
| Diethyl phthalate | ? |
| Dimethylacetamide [DMA] | ? |
| Dimethylformamide (DMF) | ? |

All information and data quoted are based upon decades of experience in the production and operation of sealing elements. This data may not be used to support any warranty claims. With its publication this latest edition supersedes all previous issues and is subject to change without further notice.

Standard: 2G. Optional: graphite or PTFE.

Size (mm): 1000 x 1500 | 1500 x 1500

Thickness (mm): 1.0 | 1.5 | 2.0 | 3.0

Other sizes and thicknesses available on request.


On length and width: $\pm 5\%$

On thickness up to 1.0 mm: ± 0.1 mm

On thickness above 1.0 mm: $\pm 10\%$

σ_{B0} DIAGRAM

DIN 28090-1



σ_{B0} diagrams represent σ_{B0} values for different gasket material thicknesses. These values indicate the maximum in-service compressive pressures which can be applied on the gasket area involved without destroying or damaging the gasket material.

P-T diagrams indicate the maximum permissible combination of internal pressure and service temperature which can be simultaneously applied for a given gasket according its material type, thickness, size and tightness class. Given the wide variety of gasket applications and service conditions, these values should only be regarded as guidance for the proper gasket assembly. In general, thinner gaskets exhibit better P-T properties.

CHEMICAL RESISTANCE CHART

The recommendations made here are intended as a guideline for the selection of a suitable gasket type. As the function and durability of products are dependent upon a number of factors, the data may not be used to support any warranty claims.

+

Recommended

?

Recommendation depends on operating conditions

-

Not recommended



DONIT TESNIT, d.o.o.

Cesta komandanta Staneta 38
1215 Medvode, Slovenia

Phone: +386 (0)1 582 33 00

Fax: +386 (0)1 582 32 06
+386 (0)1 582 32 08

Web: www.donit.eu

E-mail: info@donit.eu

For disclaimer please visit <http://donit.eu/disclaimer/>

Copyright © DONIT TESNIT, d.o.o.

All rights reserved

Date of issue: 02.2018 / TDS-BAR-05-2015